

PRODUCT	VOLUME RESISTIVITY		SURFACE RESISTIVITY		STATIC DECAY TIME		MATERIAL TYPE
	Ohm-cm	Test Method	Ohm/sq	Test Method	Seconds	Test Method	
GEL	10 ¹⁵	ASTM D257	N/A	N/A	N/A	N/A	Proprietary
AD, BD, CD Boxes except 2" x 2" (Antistatic)	10 ⁸ -10 ¹⁰	ASTM D257	10 ⁹ -10 ¹¹	ASTM D257	< 2.0	FTM No. 4046	ABS
AD, BD, CD, VR Box 2" x 2" only (Antistatic)	10 ⁹ -10 ¹¹	ASTM D257	10 ¹⁰ -10 ¹²	ASTM D257	< 2.0	FTM No. 4046	ABS
VR Lid (Antistatic)	10 ⁹ -10 ¹¹	ASTM D257	10 ¹⁰ -10 ¹²	ASTM D257	< 2.0	FTM No. 4046	ABS
AD, BD, CD Boxes except 2" x 2" (Conductive)	< 10 ⁵	ASTM D991-83	< 10 ⁶	ASTM D257-78	< 0.10	EIA-541	Polypropylene
AD, BD, CD, VR Box 2" x 2" only (Conductive)	< 10 ⁶	ASTM D257	< 10 ⁶	ASTM D257	< 0.10	FTM No. 4046	Polycarbonate
BD Tray (Conductive)	< 10 ⁶	ASTM D257	< 10 ⁶	ASTM D257	< 0.10	FTM No. 4046	Polycarbonate
VR Tray & Lid (Conductive)	< 10 ⁶	ASTM D257	< 10 ⁶	ASTM D257	< 0.10	FTM No. 4046	Polycarbonate